



**HAUSSMANN**  
NATURAL STONE

## Moca Creme

**Origin :** Portugal

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2433	II
Absorption coefficient (ASTM C97)	%	3.6	II
Porosity	%	8.92	
Compressive strength (ASTM 170)	MPa	78	III
Modulus of rupture (ASTM C99)	MPa		
Flexural strength (ASTM C880)	%	17	
Abrasion (Hd) (ASTM C241)	mm	4.2	
Resistance to fixation elements (3cm)	MPa		
Bending strength	MPa		
Freeze thaw	Cycles		
Bent Bolt Anchor Pullout test (ASTM C1354)	mm		
Pin Clip anchor Pullout test (ASTM C1354)	mm		

Recommended Uses			
Applications		Traffic wear	
Cladding	x	Not a flooring material	
Exterior pavers	x	Heavy commercial (mall)	
Interior floors	x	Low commercial (office)	x
Kitchen counters		Residential	x
Other counters	x		
Wet areas	x		

Finishes Available			
Honed	x	Dalle Rustique	
Flamed		Bush-Hammered	x
Polished		Tumbled	
Antique		Iron or sand Blasted	x
Patiné	x	Split-Face	
Leather (flamed-brushed)		Sawn	
Medieval			
Linen			

Production data			
Maximum project size	sqft	500,000	
Slab size	inch	96"x58"	
Thickness Min	inch	3/8"	
Thickness Max	inch	6"	