

Noir Sully

Origin: Belgium

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2687	Ш
Absorption coefficient (ASTM C97)	%	0.11	Ш
Porosity	%	0.28	
Compressive strength (ASTM 170)	MPa	157.9	III
Modulus of rupture (ASTM C99)	MPa	16.7	Ш
Flexural strength (ASTM C880)	%	2.87	
Abrasion (Hd) (ASTM C241)	mm		
Resistance to fixation elements (3cm)	MPa		
Bending strength	MPa		
Freeze thaw	Cycles	>240	
Bent Bolt Anchor Pullout test (ASTM C1354)	mm		
Pin Clip anchor Pullout test (ASTM C1354)	mm		

Recommended Uses				
Applications		Traffic wear		
Cladding	х	Not a flooring material		
Exterior pavers	х	Heavy commercial (mall)	X	
Interior floors	х	Low commercial (office)	Х	
Kitchen counters		Residential	Х	
Other counters	х			
Wet areas	х			

Finishes Available				
Honed	Х	Dalle Rustique		
Flamed	X	Bush-Hammered	Х	
Polished	X	Tumbled	Х	
Antique		Iron or sand Blasted		
Patiné	X	Split-Face		
Leather (flamed-brushed)		Sawn		
Medieval	X			
Linen				

Production data			
Maximum project size	sqft	50,000	
Slab size	inch	98"x54"	
Thickness Min	inch	3/8"	
Thickness Max	inch	6"	