



Atlas Grey

Origin : Morocco
Nature : Limestone

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2443	II
Absorption coefficient (ASTM C97)	%	2.5	III
Porosity	%		
Compressive strength (ASTM 170)	MPa		
Modulus of rupture (ASTM C99)	MPa		
Flexural strength (ASTM C880)	MPa	12.4	
Abrasion (Hd) (ASTM C241)	mm	23.5	
Resistance to fixation elements (3cm)	MPa		
Bending strength	MPa		
Freeze thaw	Cycles	144	
Bent Bolt Anchor Pullout test (ASTM C1354)	mm		
Pin Clip anchor Pullout test (ASTM C1354)	mm		

Recommended Uses			
Applications		Traffic wear	
Cladding	x	Not a flooring material	
Exterior pavers	x	Heavy commercial (mall)	
Interior floors	x	Low commercial (office)	x
Kitchen counters		Residential	x
Other counters	x		
Wet areas	x		

Finishes Available s = stock, c = Custom			
Honed		Linen	
Antique		Micro Bush-hammered	
Bamboo		Old world	
Bush-hammered	c	Patiné	s
Dalle Rustique		Polished	
Elektron		Sawn	c
Flamed		Split-Face	
Iron or sand Blasted		Tooled	
Leather (flamed-brushed)		Tumbled	

Production data			
Maximum project size	sqft	10,000	
Slab size	inch	98"x50"	
Thickness Min	inch	5/8"	
Thickness Max	inch	6"	