



Champagne

Origin : Turkey

| Physical properties | | | Class |
|--|-------------------|-------|-------|
| Apparent density (ASTM C97) | Kg/m ³ | 2266 | II |
| Absorption coefficient (ASTM C97) | % | 4.78 | II |
| Porosity | % | 10.83 | |
| Compressive strength (ASTM 170) | MPa | 52.71 | II |
| Modulus of rupture (ASTM C99) | MPa | | |
| Flexural strength (ASTM C880) | % | 6.1 | |
| Abrasion (Hd) (ASTM C241) | mm | | |
| Resistance to fixation elements (3cm) | MPa | | |
| Bending strength | MPa | | |
| Freeze thaw | Cycles | | |
| Bent Bolt Anchor Pullout test (ASTM C1354) | mm | | |
| Pin Clip anchor Pullout test (ASTM C1354) | mm | | |

| Recommended Uses | | | |
|------------------|---|-------------------------|---|
| Applications | | Traffic wear | |
| Cladding | x | Not a flooring material | |
| Exterior pavers | x | Heavy commercial (mall) | |
| Interior floors | x | Low commercial (office) | |
| Kitchen counters | | Residential | x |
| Other counters | x | | |
| Wet areas | x | | |

| Finishes Available | | | |
|--------------------------|---|----------------------|---|
| Honed | x | Dalle Rustique | |
| Flamed | | Bush-Hammered | x |
| Polished | | Tumbled | |
| Antique | | Iron or sand Blasted | x |
| Patiné | x | Split-Face | x |
| Leather (flamed-brushed) | | Sawn | |
| Medieval | | | |
| Linen | | | |

| Production data | | | |
|----------------------|------|----------|--|
| Maximum project size | sqft | 200,000 | |
| Slab size | inch | 100"x55" | |
| Thickness Min | inch | 3/8" | |
| Thickness Max | inch | 6" | |