



**HAUSSMANN**  
NATURAL STONE

## Côte d'Azur

**Origin :** Spain

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2670	III
Absorption coefficient (ASTM C97)	%	0.34	III
Porosity	%		
Compressive strength (ASTM 170)	MPa	88.10	III
Modulus of rupture (ASTM C99)	MPa	1.8	III
Flexural strength (ASTM C880)	%	18.61	
Abrasion (Hd) (ASTM C241)	mm	20	
Resistance to fixation elements (3cm)	MPa		
Bending strength	MPa		
Freeze thaw	Cycles	> 48	
Bent Bolt Anchor Pullout test (ASTM C1354)	mm		
Pin Clip anchor Pullout test (ASTM C1354)	mm		

Recommended Uses			
Applications		Traffic wear	
Cladding	x	Not a flooring material	
Exterior pavers	x	Heavy commercial (mall)	x
Interior floors	x	Low commercial (office)	x
Kitchen counters	x	Residential	x
Other counters	x		
Wet areas	x		

Finishes Available			
Honed	x	Dalle Rustique	
Flamed		Bush-Hammered	
Polished		Tumbled	
Antique		Iron or sand Blasted	
Patiné		Split-Face	
Leather (flamed-brushed)	x	Sawn	
Medieval			
Linen			

Production data			
Maximum project size	sqft	100,000	
Slab size	inch	100"x60"	
Thickness Min	inch	3/8"	
Thickness Max	inch	4"	