



HAUSSMANN
NATURAL STONE

Jura Grey

Origin : Germany

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2600	III
Absorption coefficient (ASTM C97)	%	0.93	III
Porosity	%		
Compressive strength (ASTM 170)	MPa	167	III
Modulus of rupture (ASTM C99)	MPa		
Flexural strength (ASTM C880)	%	18.8	
Abrasion (Hd) (ASTM C241)	mm	8.9	
Resistance to fixation elements (3cm)	MPa		
Bending strength	MPa		
Freeze thaw	Cycles		
Bent Bolt Anchor Pullout test (ASTM C1354)	mm		
Pin Clip anchor Pullout test (ASTM C1354)	mm		

Recommended Uses			
Applications		Traffic wear	
Cladding	x	Not a flooring material	
Exterior pavers	x	Heavy commercial (mall)	x
Interior floors	x	Low commercial (office)	x
Kitchen counters	x	Residential	x
Other counters	x		
Wet areas	x		

Finishes Available			
Honed	x	Dalle Rustique	
Flamed		Bush-Hammered	x
Polished	x	Tumbled	
Antique		Iron or sand Blasted	x
Patiné	x	Split-Face	x
Leather (flamed-brushed)		Sawn	
Medieval			
Linen			

Production data			
Maximum project size	sqft	500,000	
Slab size	inch	98"x50"	
Thickness Min	inch	3/8"	
Thickness Max	inch	2"	