



Lanvignes

Origin : France
Nature : Limestone

Physical properties			Class
Apparent density (ASTM C97)	Kg/m3	2140	I
Absorption coefficient (ASTM C97)	%		
Porosity	%	20.7	
Compressive strength (ASTM 170)	MPa	72	III
Modulus of rupture (ASTM C99)	MPa		
Flexural strength (ASTM C880)	MPa		
Abrasion (Hd) (ASTM C241)	mm	30.9	
Resistance to fixation elements (3cm)	MPa	94	
Bending strength	MPa	8	
Freeze thaw	Cycles	>240	
Bent Bolt Anchor Pullout test (ASTM C1354)	mm		
Pin Clip anchor Pullout test (ASTM C1354)	mm		

Recommended Uses			
Applications		Traffic wear	
Cladding	x	Not a flooring material	
Exterior pavers	x	Heavy commercial (mall)	
Interior floors	x	Low commercial (office)	x
Kitchen counters		Residential	x
Other counters	x		
Wet areas	x		

Finishes Available s = stock, c = Custom			
Honed	c	Linen	
Antique		Micro Bush-hammered	
Bamboo		Old world	
Bush-hammered	c	Patiné	s
Dalle Rustique		Polished	
Elektron		Sawn	c
Flamed		Split-Face	c
Iron or sand Blasted	c	Tooled	
Leather (flamed-brushed)		Tumbled	c

Production data		
Maximum project size	sqft	100,000
Slab size	inch	96"x52"
Thickness Min	inch	3/8"
Thickness Max	inch	6"